

Technical Data Sheet

Duresco NU 6210 V

Product Characteristics: Glass fibre reinforced epoxy moulding compound

with very good mechanical properties and excellent

thermal shock resistance

Applications: Encapsulation of electrical devices, e.g.

Electronic, Sensors, Solenoids, Stators

Processing methods: Injection and transfer moulding

Shelf life: 12 months at temperatures ≤ 8°C

The information given in this publication are typical values based on the present state of our knowledge but any conclusions and recommendations are made without liability on our part. Buyers and users should make their own assessment of our products under their own conditions and for their own requirements.



Technical Data Sheet

Mechanical Properties:

| | Standard | Unit | Value |
|---------------------------|-----------|-------|--------|
| Tensile strength | ISO 527 | MPa | 100 |
| Flexural strength | ISO 178 | MPa | 190 |
| Surface strain | ISO 178 | % | 1.4 |
| E-modulus (flexural test) | ISO 178 | MPa | 17'000 |
| Impact strength | ISO 179-1 | kJ/m² | 22 |

General and Thermal Properties:

| | Standard | Unit | Value |
|----------------------------------|-------------|-------------------|-------|
| Density | DIN 53479 | g/cm ³ | 1.95 |
| Water absorption (100°C/30min) | ISO 62 | % | 0.06 |
| Glass transition temperature | ISO 6721-7 | °C | 120 |
| Thermal conductivity | ISO 8894 | W/mK | 0.85 |
| Coefficient of thermal expansion | ISO 11359-2 | ppm/K, (20–110°C) | 20 |

Electrical Properties:

| | Standard | Unit | Value |
|------------------------------------|-----------|-----------------|------------------|
| Surface resistivity | IEC 60093 | Ω, 25°C | 10 ¹⁶ |
| Volume resistivity | IEC 60093 | Ωcm, 25°C | 10 ¹⁵ |
| Dielectric loss factor tan δ | IEC 60250 | % , 50 Hz, 25°C | 1.6 |
| Dielectric constant ε _r | IEC 60250 | , 50 Hz, 25°C | 5.0 |
| Comparative tracking index | IEC 60112 | CTI | 300 |