

Technical Data Sheet

Duresco NU 463 V

Product Characteristics:	Glass fibre reinforced encapsulation epoxy moulding compound with very good mechanical properties and excellent crack resistance
Colour:	Black
Applications:	Encapsulation of electrical devices e.g. Solenoids, Stators, Transformers
Processing methods:	Transfer and injection moulding
Shelf life:	12 months at temperatures below 8°C

The information given in this publication is based on the present state of our knowledge but any conclusions and recommendations are made without liability on our part. Buyers and users should make their own assessment of our products under their own conditions and for their own requirements.

Version 7, January 2018

Technical Data Sheet

Mechanical Properties:

	Standard	Unit	Value
Tensile strength	ISO 527	MPa	110
Flexural strength	ISO 178	MPa	180
Surface strain	ISO 178	%	1.5
E-modulus (flexural test)	ISO 178	MPa	15'000
Impact strength	ISO 179-1	kJ/m ²	16
Notched impact strength	ISO 179-1	kJ/m ²	3

General and Thermal Properties:

	Standard	Unit	Value
Density	DIN 53479	g/cm ³	1.9
Water absorption (100°C/30min)	ISO 62	%	0.08
Glass transition temperature	ISO 6721-7	°C	110
Temperature-time limit TI (flexural strength)	IEC 60216	°C, 20'000h	170
Thermal conductivity	ISO 8894	W/mK	0.85
Coefficient of thermal expansion	ISO 11359-2	ppm/K, 20-90°C	24

Electrical Properties:

	Standard	Unit	Value
Volume resistivity	IEC 60093	Ωcm, 25°C	10 ¹⁵
Dielectric loss factor tan δ	IEC 60250	%, 50 Hz, 25°C	1.3
Dielectric constant ε _r	IEC 60250	-- , 50 Hz, 25°C	4.7
Electric strength (3mm plate)	IEC 60243-1	kV/mm	23
Comparative tracking index	IEC 60112	CTI	250
Comparative tracking index	IEC 60112	CTI-M	225